


| | | | | |
|---|---|----------------------|-----------------|---------|
|  | Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom | | Version: 2012-3 | |
| | | | 18 | 1162 |
| | | | CPR-GB-0017 | |
| | | | www.nynas.com | |
| EN 12591:2009 | | Paving Grade Bitumen | | 100/150 |
| Nybit E 125 | | | | |
| Construction and maintenance of roads, airfields and other paved areas | | | | |
| | | | | |
| Property | Method | Unit | Values | |
| Penetration at 25 °C | EN 1426 | mm/10 | 100-150 | |
| Softening Point Ring & Ball | EN 1427 | °C | 39-47 | |
| | | | | |
| RESISTANCE TO HARDENING AT 163 °C | | | | |
| Retained penetration at 25 °C | EN 1426 | % | ≥ 43 | |
| Increase in softening point | EN 1427 | °C | ≤ 10 | |
| | | | | |
| Penetration index | Annex A | | -1.5 to + 0.7 | |
| Dynamic viscosity at 60 °C | EN 13302 | Pa • s | NR | |
| Fraass Breaking point | EN 12593 | °C | ≤ -12 | |
| | | | | |
| Regulated Dangerous Substances | | | NPD | |
| | | | | |