

	Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom		Version: 2012-3																																									
			18	1162																																								
			CPR-GB-0001																																									
			www.nynas.com																																									
EN 12591:2009		Paving Grade Bitumen		20/30																																								
Nynas 20/30																																												
Construction and maintenance of roads, airfields and other paved areas																																												
<table border="1"> <thead> <tr> <th>Property</th> <th>Method</th> <th>Unit</th> <th>Values</th> </tr> </thead> <tbody> <tr> <td>Penetration at 25 °C</td> <td>EN 1426</td> <td>mm/10</td> <td>20-30</td> </tr> <tr> <td>Softening Point Ring & Ball</td> <td>EN 1427</td> <td>°C</td> <td>55-63</td> </tr> <tr> <td colspan="4">RESISTANCE TO HARDENING AT 163 °C</td> </tr> <tr> <td>Retained penetration at 25 °C</td> <td>EN 1426</td> <td>%</td> <td>≥ 55</td> </tr> <tr> <td>Increase in softening point</td> <td>EN 1427</td> <td>°C</td> <td>≤ 8</td> </tr> <tr> <td>Penetration index</td> <td>Annex A</td> <td></td> <td>-1.5 to + 0.7</td> </tr> <tr> <td>Dynamic viscosity at 60 °C</td> <td>EN 13302</td> <td>Pa • s</td> <td>NR</td> </tr> <tr> <td>Fraass Breaking point</td> <td>EN 12593</td> <td>°C</td> <td>NR</td> </tr> <tr> <td colspan="3">Regulated Dangerous Substances</td> <td>NPD</td> </tr> </tbody> </table>					Property	Method	Unit	Values	Penetration at 25 °C	EN 1426	mm/10	20-30	Softening Point Ring & Ball	EN 1427	°C	55-63	RESISTANCE TO HARDENING AT 163 °C				Retained penetration at 25 °C	EN 1426	%	≥ 55	Increase in softening point	EN 1427	°C	≤ 8	Penetration index	Annex A		-1.5 to + 0.7	Dynamic viscosity at 60 °C	EN 13302	Pa • s	NR	Fraass Breaking point	EN 12593	°C	NR	Regulated Dangerous Substances			NPD
Property	Method	Unit	Values																																									
Penetration at 25 °C	EN 1426	mm/10	20-30																																									
Softening Point Ring & Ball	EN 1427	°C	55-63																																									
RESISTANCE TO HARDENING AT 163 °C																																												
Retained penetration at 25 °C	EN 1426	%	≥ 55																																									
Increase in softening point	EN 1427	°C	≤ 8																																									
Penetration index	Annex A		-1.5 to + 0.7																																									
Dynamic viscosity at 60 °C	EN 13302	Pa • s	NR																																									
Fraass Breaking point	EN 12593	°C	NR																																									
Regulated Dangerous Substances			NPD																																									