

	Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom		Version: 2012-3	
			18	1162
			CPR-GB-0009	
			www.nynas.com	
EN 12591:2009	Paving Grade Bitumen		250/330	
Nynas 250/330				
Construction and maintenance of roads, airfields and other paved areas				
Property	Method	Unit	Values	
Penetration at 25 °C	EN 1426	mm/10	250-330	
Softening Point Ring & Ball	EN 1427	°C	30-38	
RESISTANCE TO HARDENING AT 163 °C				
Viscosity ratio at 60 °C			NR	
Increase in softening point	EN 1427	°C	≤ 11	
Fraass Breaking point	EN 12593	°C	≤ -16	
Regulated Dangerous Substances			NPD	