

	Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom		Version: 2012-5	
			18	1162
			CPR-GB-0049	
			www.nynas.com	
EN 13808:2013		Emulsion		C70BP3
Nynas Duramuls				
Surface dressing				
<b>Property</b>	<b>Method</b>	<b>Unit</b>	<b>Values</b>	
EMULSION				
Breaking value	EN 13075-1		70-155	
Efflux time 4 mm at 40 °C	EN 12846-1	s	5-70	
Adhesivity with reference aggregate	EN 13614		≥ 90	
RECOVERED BINDER				
Penetration at 25 °C	EN 1426	mm/10	≤ 220	
Softening Point Ring & Ball	EN 1427	°C	≥ 50	
Cohesion - Pendulum Vialit	EN 13588	J/cm2	NR	
STABILISED BINDER				
Penetration at 25 °C	EN 1426	mm/10	≤ 150	
Softening Point Ring & Ball	EN 1427	°C	≥ 50	
Cohesion - Pendulum Vialit	EN 13588	J/cm2	≥ 1.2	
Regulated Dangerous Substances			NPD	