

	Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom		Version: 2012-3	
			18	1162
			CPR-GB-0037	
			www.nynas.com	
EN 14023:2010		Polymer modified Bitumen		25/55-75
Nynas Endura Z4				
Construction and maintenance of roads, airfields and other paved areas				
Property	Method	Unit	Values	
Penetration at 25 °C	EN 1426	mm/10	25-55	
Softening Point Ring & Ball	EN 1427	°C	>75	
Cohesion - Force Ductility at 10 °C	EN 13589	J/cm2	≥ 3	
RESISTANCE TO HARDENING AT 163 °C				
Retained penetration at 25 °C	EN 1426	%	≥ 50	
Increase in softening point	EN 1427	°C	≤ 8	
Fraass Breaking point	EN 12593	°C	NR	
Elastic Recovery at 25 °C	EN 13398	%	≥60	
Regulated Dangerous Substances			NPD	