

	Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom		Version: 2012-5	
			18	1162
			CPR-GB-0055	
			www.nynas.com	
EN 13808:2013		Emulsion		C65BP5
Nynas Micromuls				
Sealing				
Property	Method	Unit	Values	
EMULSION				
Breaking value	EN 13075-1		> 170	
Efflux time 2 mm at 40 °C	EN 12846-1	s	15-70	
Adhesivity with reference aggregate	EN 13614		≥ 90	
RECOVERED BINDER				
Penetration at 25 °C	EN 1426	mm/10	≤ 150	
Softening Point Ring & Ball	EN 1427	°C	≥ 50	
Cohesion - Force Ductility at 5 °C	EN 13589	J/cm2	≥ 1	
STABILISED BINDER				
Penetration at 25 °C	EN 1426	mm/10	≤ 100	
Softening Point Ring & Ball	EN 1427	°C	≥ 55	
Cohesion - Force Ductility at 5 °C	EN 13589	J/cm2	≥ 2	
Regulated Dangerous Substances			NPD	