

	Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom	Version: 2012-3																																									
		18	1162																																								
		CPR-GB-0039																																									
		www.nynas.com																																									
EN 14023:2010	Polymer modified Bitumen	25/55-60																																									
Nypol 46																																											
Construction and maintenance of roads, airfields and other paved areas																																											
<table border="1"> <thead> <tr> <th>Property</th> <th>Method</th> <th>Unit</th> <th>Values</th> </tr> </thead> <tbody> <tr> <td>Penetration at 25 °C</td> <td>EN 1426</td> <td>mm/10</td> <td>25-55</td> </tr> <tr> <td>Softening Point Ring & Ball</td> <td>EN 1427</td> <td>°C</td> <td>>60</td> </tr> <tr> <td>Cohesion - Force Ductility at 10 °C</td> <td>EN 13589</td> <td>J/cm2</td> <td>≥ 3</td> </tr> <tr> <td colspan="4">RESISTANCE TO HARDENING AT 163 °C</td> </tr> <tr> <td>Retained penetration at 25 °C</td> <td>EN 1426</td> <td>%</td> <td>≥ 50</td> </tr> <tr> <td>Increase in softening point</td> <td>EN 1427</td> <td>°C</td> <td>≤ 8</td> </tr> <tr> <td>Fraass Breaking point</td> <td>EN 12593</td> <td>°C</td> <td>NR</td> </tr> <tr> <td>Elastic Recovery at 25 °C</td> <td>EN 13398</td> <td>%</td> <td>≥70</td> </tr> <tr> <td colspan="3">Regulated Dangerous Substances</td> <td>NPD</td> </tr> </tbody> </table>				Property	Method	Unit	Values	Penetration at 25 °C	EN 1426	mm/10	25-55	Softening Point Ring & Ball	EN 1427	°C	>60	Cohesion - Force Ductility at 10 °C	EN 13589	J/cm2	≥ 3	RESISTANCE TO HARDENING AT 163 °C				Retained penetration at 25 °C	EN 1426	%	≥ 50	Increase in softening point	EN 1427	°C	≤ 8	Fraass Breaking point	EN 12593	°C	NR	Elastic Recovery at 25 °C	EN 13398	%	≥70	Regulated Dangerous Substances			NPD
Property	Method	Unit	Values																																								
Penetration at 25 °C	EN 1426	mm/10	25-55																																								
Softening Point Ring & Ball	EN 1427	°C	>60																																								
Cohesion - Force Ductility at 10 °C	EN 13589	J/cm2	≥ 3																																								
RESISTANCE TO HARDENING AT 163 °C																																											
Retained penetration at 25 °C	EN 1426	%	≥ 50																																								
Increase in softening point	EN 1427	°C	≤ 8																																								
Fraass Breaking point	EN 12593	°C	NR																																								
Elastic Recovery at 25 °C	EN 13398	%	≥70																																								
Regulated Dangerous Substances			NPD																																								