

	Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom	Version: 2012-3	
		18	1162
		CPR-GB-0061	
		www.nynas.com	
EN 14023:2010	Polymer modified Bitumen	65/105-45	
Nypol S 89 A			
Construction and maintenance of roads, airfields and other paved areas			
Property	Method	Unit	Values
Penetration at 25 °C	EN 1426	mm/10	65-105
Softening Point Ring & Ball	EN 1427	°C	>45
Cohesion - Force Ductility at 5 °C	EN 13589	J/cm2	≥ 2
RESISTANCE TO HARDENING AT 163 °C			
Retained penetration at 25 °C	EN 1426	%	≥ 50
Increase in softening point	EN 1427	°C	≤ 8
Fraass Breaking point	EN 12593	°C	NR
Elastic Recovery at 25 °C	EN 13398	%	≥50
Regulated Dangerous Substances			NPD