

	Nynas UK AB North Road, Ellesmere Port CH65 1AJ, United Kingdom		Version: 2015-2																																											
			18	1162																																										
			CPR-GB-0075																																											
			www.nynas.com																																											
EN 14023:2010	Polymer modified Bitumen		75/130-75																																											
Nytherm PMB 103																																														
Construction and maintenance of roads, airfields and other paved areas																																														
<table border="1"> <thead> <tr> <th>Property</th> <th>Method</th> <th>Unit</th> <th>Values</th> </tr> </thead> <tbody> <tr> <td>Penetration at 25 °C</td> <td>EN 1426</td> <td>mm/10</td> <td>75-130</td> </tr> <tr> <td>Softening Point Ring &amp; Ball</td> <td>EN 1427</td> <td>°C</td> <td>&gt;75</td> </tr> <tr> <td>Cohesion - Force Ductility at 10 °C</td> <td>EN 13589</td> <td>J/cm2</td> <td>≥ 3</td> </tr> <tr> <td colspan="5">RESISTANCE TO HARDENING AT 163 °C</td> </tr> <tr> <td>Retained penetration at 25 °C</td> <td>EN 1426</td> <td>%</td> <td>≥ 50</td> </tr> <tr> <td>Increase in softening point</td> <td>EN 1427</td> <td>°C</td> <td>≤ 8</td> </tr> <tr> <td>Fraass Breaking point</td> <td>EN 12593</td> <td>°C</td> <td>NR</td> </tr> <tr> <td>Elastic Recovery at 25 °C</td> <td>EN 13398</td> <td>%</td> <td>≥80</td> </tr> <tr> <td colspan="3">Regulated Dangerous Substances</td> <td colspan="2">NPD</td> </tr> </tbody> </table>					Property	Method	Unit	Values	Penetration at 25 °C	EN 1426	mm/10	75-130	Softening Point Ring & Ball	EN 1427	°C	>75	Cohesion - Force Ductility at 10 °C	EN 13589	J/cm2	≥ 3	RESISTANCE TO HARDENING AT 163 °C					Retained penetration at 25 °C	EN 1426	%	≥ 50	Increase in softening point	EN 1427	°C	≤ 8	Fraass Breaking point	EN 12593	°C	NR	Elastic Recovery at 25 °C	EN 13398	%	≥80	Regulated Dangerous Substances			NPD	
Property	Method	Unit	Values																																											
Penetration at 25 °C	EN 1426	mm/10	75-130																																											
Softening Point Ring & Ball	EN 1427	°C	>75																																											
Cohesion - Force Ductility at 10 °C	EN 13589	J/cm2	≥ 3																																											
RESISTANCE TO HARDENING AT 163 °C																																														
Retained penetration at 25 °C	EN 1426	%	≥ 50																																											
Increase in softening point	EN 1427	°C	≤ 8																																											
Fraass Breaking point	EN 12593	°C	NR																																											
Elastic Recovery at 25 °C	EN 13398	%	≥80																																											
Regulated Dangerous Substances			NPD																																											