

Nybit E 125

Nybit E 125 is a bitumen specially formulated for emulsion production and is produced according EN 12591.

Paving Grade 100/150

Table 1 : Specifications

	Test description	Method	Unit	Min	Max
Consistency at intermediate service temperature	Penetration at 25°C	EN 1426	mm/10	100	150
Consistency at elevated service temperature	Softening Point	EN 1427	°C	39	47
Resistance to hardening at 163°C	Change in mass	EN 12607-1	%	-	0.80
	Retained penetration	EN 1426	%	43	-
	Softening point after hardening	EN 1427	°C	41	-

Table 2 : Additional information

	Test description	Method	Unit	Min	Max
Safety & Handling *	Minimum pumping temperature	-	°C	105	-
	Typical handling / storage temperature	-	°C	135	155
	Maximum handling / storage temperature	-	°C	-	190
	Flashpoint (COC)	EN ISO 2592	°C	230	-
Technical characteristic	Density at 25°C	EN 15326	g/cm ³	1.019 ¹	-
	Kinematic viscosity at 135 °C	EN 12595	mm ² /s	175	-
	Solubility	EN 12592	%	99.0	-

* For specific information on binder handling and storage please refer to the Product Information and Safety Data sheets.

¹ Nynas Specification

This product fulfils EN 12591 requirements for paving grade bitumen 100/150 and is CE marked

Nynas UK
North Road, Ellesmere Port
CH65 1AJ South Wirral
United Kingdom (UK)
T +44 151 327 31 71
F +44 151 327 61 95
E bitumen.uk@nynas.com
W www.nynas.com

Nynas UK
East Camperdown Street
DD1 3LG Dundee
United Kingdom (UK)
T +44 1382 46 22 11
F +44 1382 45 03 08

Although the data reported in the present document is, to the best of our knowledge, accurate and reliable, Nynas shall not be liable for any loss or damage that may occur.

SdS available on nynas.com